



US011420182B2

(12) **United States Patent**
Bai et al.

(10) **Patent No.:** **US 11,420,182 B2**

(45) **Date of Patent:** **Aug. 23, 2022**

(54) **HYDROPHOBIC SORBENTS FOR CO₂/H₂O DISPLACEMENT DESORPTION APPLICATIONS**

(52) **U.S. Cl.**
CPC **B01J 20/041** (2013.01); **B01D 53/02** (2013.01); **B01J 20/08** (2013.01); **B01J 20/103** (2013.01);

(71) Applicants: **ExxonMobil Technology and Engineering Company**, Annandale, NJ (US); **TDA Research, Inc.**, Wheat Ridge, CO (US)

(Continued)
(58) **Field of Classification Search**
CPC B01J 20/041; B01J 20/08; B01J 20/103; B01J 20/22; B01J 20/3078; B01J 20/3204;

(72) Inventors: **Chuansheng Bai**, Phillipsburg, NJ (US); **Majosefina Cunningham**, Whitehall, PA (US); **Patrick P. McCall**, Matawan, NJ (US); **Hans Thomann**, Bedminster, NJ (US); **Jeannine Elizabeth Elliott**, Superior, CO (US); **Vinh Nguyen**, Arvada, CO (US)

(Continued)

(73) Assignees: **ExxonMobile Technology and Engineering Company**, Annandale, NJ (US); **TDA Research, Inc. W**, Wheat Ridge, CO (US)

(56) **References Cited**
U.S. PATENT DOCUMENTS

5,378,440 A 1/1995 Herbst et al.
9,446,343 B2 9/2016 Elliott et al.

(Continued)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 749 days.

OTHER PUBLICATIONS

Castricum, Hessel L. et al., Hydrophobisation of mesoporous γ -Al₂O₃ with organochlorosilanes-efficiency and structure, Microporous and Mesoporous Materials, 2005, pp. 1-9, vol. 83, Elsevier.

(Continued)

(21) Appl. No.: **15/910,212**

Primary Examiner — James A Fiorito

(22) Filed: **Mar. 2, 2018**

(74) *Attorney, Agent, or Firm* — Troutman Pepper Hamilton Sanders LLP; John A. Morrissett; Scott A. Bergeson

(65) **Prior Publication Data**

US 2018/0250653 A1 Sep. 6, 2018

Related U.S. Application Data

(60) Provisional application No. 62/466,811, filed on Mar. 3, 2017.

(57) **ABSTRACT**


The disclosure generally relates to CCS sorbents, particularly for CO₂/H₂O displacement desorption process. The sorbent includes an aluminum oxide support and an alkali metal salt impregnated on the support, and a silicon modification of the sorbent to reduce water uptake by the sorbent and make it more hydrophobic. The silicon modification can be an organosilyl moiety added after the initial sorbent is complete, or a silica source added to the aluminum oxide structure, typically via impregnation. The sorbents demonstrate better H₂O/CO₂ ratios. Compositions and methods of making are disclosed.

(51) **Int. Cl.**

B01J 20/04 (2006.01)
B01J 20/10 (2006.01)
B01J 20/08 (2006.01)
B01J 20/34 (2006.01)
B01J 20/32 (2006.01)

(Continued)

13 Claims, 2 Drawing Sheets



- (51) **Int. Cl.**
B01J 20/30 (2006.01)
B01D 53/02 (2006.01)
B01J 20/22 (2006.01)

- (52) **U.S. Cl.**
 CPC *B01J 20/22* (2013.01); *B01J 20/3078*
 (2013.01); *B01J 20/3204* (2013.01); *B01J*
20/3234 (2013.01); *B01J 20/3433* (2013.01);
B01J 20/3466 (2013.01); *B01D 2253/104*
 (2013.01); *B01D 2253/106* (2013.01); *B01D*
2253/1124 (2013.01); *B01D 2253/20*
 (2013.01); *B01D 2253/25* (2013.01); *B01D*
2257/504 (2013.01); *B01D 2258/0283*
 (2013.01); *B01D 2259/40086* (2013.01)

- (58) **Field of Classification Search**
 CPC B01J 20/3234; B01J 20/3433; B01J
 20/3466; B01D 53/02
 See application file for complete search history.

- (56) **References Cited**
 U.S. PATENT DOCUMENTS

9,504,955	B2	11/2016	Elliott et al.
9,527,029	B2	12/2016	Elliott et al.
9,539,540	B2	1/2017	Elliott et al.
2002/0157535	A1	10/2002	Kanazirev et al.
2003/0232722	A1	12/2003	Kato et al.
2004/0011198	A1	1/2004	Keefer et al.
2015/0321166	A1	11/2015	Kim et al.

OTHER PUBLICATIONS

International Search Report and Written Opinion issued in related International Application No. PCT/US18/20639 dated May 16, 2018.




Figure 1




Figure 2




Figure 3

1

HYDROPHOBIC SORBENTS FOR CO₂/H₂O DISPLACEMENT DESORPTION APPLICATIONS

CROSS REFERENCE TO RELATED APPLICATIONS

This application claims the benefit of U.S. Provisional Application No. 62/466,811, filed 3 Mar. 2017, which is entirely incorporated herein by reference.

STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH

Portions of this disclosure were made with government support under Contract No. DE-FE0012870, awarded by the Department of Energy. The government may have certain rights in the invention.

TECHNICAL FIELD

The various embodiments of the disclosure relate generally to methods for making and compositions of hydrophobic sorbents. It is particularly useful for preparing sorbents for CO₂/H₂O displacement desorption processes, in which the sorbent has been made more hydrophobic by the including of silicon sources.

BACKGROUND

Fossil fuels currently supply the majority of world's energy needs and their combustion is the largest source of anthropogenic carbon dioxide emissions. Carbon dioxide is a greenhouse gas and is believed to contribute to global climate change. Concern over global climate warming has led to interest in capturing CO₂ emissions from the combustion of fossil fuels. The quantities of combustion gas produced in electric power generation are large because of the scale of furnaces and turbines utilized. One measure of the scale of these operations is the amount of CO₂ produced in a typical 500 Megawatt power plant, for coal fired power generation, the rate of CO₂ production is on the order of 100 kg per second; for gas fired power production it is more like 50 kg per second.

CO₂ can be removed from combustion flue gas streams by various methods, often referred to a carbon capture and sequestration (CCS.) The challenge for CO₂ capture from flue gas is to do it efficiently to minimize the cost. All post-combustion CO₂ capture technologies suffer from the disadvantages that the CO₂ in the flue gas is present at low pressure (1 atmospheric pressure) and in low concentrations (3 to 15%). A large amount of energy is needed to separate CO₂. Developing methods that minimize the amount of energy and other costs will be necessary if CO₂ removal from flue gas is to be economical. Methods for the removal of CO₂ from flue gas streams include adsorption with a solvent, adsorption with a sorbent, membrane separation, and cryogenic fractionation and combinations thereof. In absorption/adsorption processes to capture CO₂, the energy needed to regenerate the sorbent or solvent is also a large cost element.

CO₂ displacement desorption process uses a competitive adsorption of H₂O to drive off adsorbed CO₂ on sorbent. During CO₂ capturing step, CO₂ of the flue gas displaces the adsorbed H₂O on the sorbent. Displacement desorption

2

swings the concentrations of H₂O and CO₂. It is an isothermal process and has no need for pressure swing.

BRIEF SUMMARY

The various embodiments of the disclosure relate generally to methods for preparing and compositions of silicon-modified sorbents.

An embodiment of the disclosure can be a silicon-modified CO₂/H₂O displacement desorption sorbent, comprising an aluminum compound support; an alkali metal salt; and a silicon source capping hydroxyl positions on the aluminum compound support.

In some embodiments, the silicon source can be 5% to 20% by weight of silica impregnated on the aluminum support. The silicon source can be 7% to 15% by weight of silica impregnated on the aluminum support.

In some embodiments, the silicon source comprises an organosilyl moiety. The organo silyl moiety can be a triorganosilyl halide or triflate. In some embodiments, the organo silyl moiety can be a trialkyl silyl moiety. The alkyl fragment of the trialkylsilyl moiety can be methyl, ethyl, or propyl, or combinations thereof. In some embodiments, the trialkyl silyl moiety is a trialkylsilyl halide or triflate. The organosilyl moiety can be trimethylsilyl chloride.

An embodiment of the disclosure can be a method for reducing parasitic water sorption/desorption for CO₂/H₂O displacement desorption sorbents, comprising surface modifying a sorbent with a silicon source. The sorbent can be an aluminum compound impregnated with an alkali metal; and the silicon source can be either an organosilyl moiety added to the sorbent after impregnating with the alkali metal; or a silica added to the aluminum compound prior to impregnating with the alkali metal.

In some embodiments, the silicon source comprises an organosilyl moiety. The organo silyl moiety can be a triorganosilyl halide or triflate. In some embodiments, the organo silyl moiety can be a trialkyl silyl moiety. The alkyl fragment of the trialkylsilyl moiety can be methyl, ethyl, or propyl, or combinations thereof. In some embodiments, the trialkyl silyl moiety is a trialkylsilyl halide or triflate. The organosilyl moiety can be trimethylsilyl chloride.

In some embodiments, the silicon source can be 5% to 20% by weight of silica impregnated on the aluminum support. The silicon source can be 7% to 15% by weight of silica impregnated on the aluminum support.

An embodiment of the disclosure can be a method for preparing a hydrophobic CO₂/H₂O displacement desorption sorbent, including the steps of impregnating an aluminum compound support with silica; drying and then calcining the silica-impregnated support; depositing an alkali metal salt on the silica-aluminum support; and calcining the support to form the sorbent.

In some embodiments, the silicon source can be 5% to 20% by weight of silica impregnated on the aluminum support. The silicon source can be 7% to 15% by weight of silica impregnated on the aluminum support.

In some embodiments, the aluminum compound can be aluminum oxide, aluminum oxide hydroxide, aluminum hydroxide, boehmite, or pseudoboehmite. In some embodiments, the alkali metal salt can be a potassium salt, a sodium salt, or a lithium salt, or a combination thereof. In some embodiments, the alkali metal salt can be greater than about 5 weight % of the sorbent as M₂O, or can be greater than about 8 weight % of the sorbent as M₂O.

An embodiment of the disclosure can be a method for preparing a hydrophobic CO₂/H₂O displacement desorption

sorbent, including the steps of preparing an aluminum compound mixture; drying and then calcining the mixture to form a support; depositing an alkali metal salt on the support; and calcining the support to form the sorbent, and treating the sorbent with an organo silyl moiety.

In some embodiments, the silicon source comprises an organosilyl moiety. The organo silyl moiety can be a triorganosilyl halide or triflate. In some embodiments, the organo silyl moiety can be a trialkyl silyl moiety. The alkyl fragment of the trialkylsilyl moiety can be methyl, ethyl, or propyl, or combinations thereof. In some embodiments, the trialkyl silyl moiety is a trialkylsilyl halide or triflate. The organosilyl moiety can be trimethylsilyl chloride.

In some embodiments, the aluminum compound can be aluminum oxide, aluminum oxide hydroxide, aluminum hydroxide, boehmite, or pseudoboehmite. In some embodiments, the alkali metal salt can be a potassium salt, a sodium salt, or a lithium salt, or a combination thereof. In some embodiments, the alkali metal salt can be greater than about 5 weight % of the sorbent as M_2O , or can be greater than about 8 weight % of the sorbent as M_2O .

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates a simplified system of CO_2/H_2O displacement desorption system in which a sorbent of the disclosure would be applied, in accordance with an exemplary embodiment of the disclosure.

FIG. 2 illustrates the effect of TMS chloride treatment on $K_2CO_3+Na_2CO_3/Al_2O_3$ supports, in accordance with an exemplary embodiment of the disclosure.

FIG. 3 illustrates the effect of silica and aluminum type supports, including $K_2CO_3+Na_2CO_3$ supported on SiO_2/Al_2O_3 and Al_2O_3/SiO_2 , in accordance with an exemplary embodiment of the disclosure.

DETAILED DESCRIPTION

Although preferred embodiments of the disclosure are explained in detail, it is to be understood that other embodiments are contemplated. Accordingly, it is not intended that the disclosure is limited in its scope to the details of construction and arrangement of components set forth in the following description or illustrated in the drawings. The disclosure is capable of other embodiments and of being practiced or carried out in various ways. Also, in describing the preferred embodiments, specific terminology will be resorted to for the sake of clarity.

It must also be noted that, as used in the specification and the appended claims, the singular forms "a," "an" and "the" include plural referents unless the context clearly dictates otherwise.

Also, in describing the preferred embodiments, terminology will be resorted to for the sake of clarity. It is intended that each term contemplates its broadest meaning as understood by those skilled in the art and includes all technical equivalents which operate in a similar manner to accomplish a similar purpose.

Ranges can be expressed herein as from "about" or "approximately" one particular value and/or to "about" or "approximately" another particular value. When such a range is expressed, another embodiment includes from the one particular value and/or to the other particular value.

By "comprising" or "containing" or "including" is meant that at least the named compound, element, particle, or method step is present in the composition or article or method, but does not exclude the presence of other com-

pounds, materials, particles, method steps, even if the other such compounds, material, particles, method steps have the same function as what is named.

It is also to be understood that the mention of one or more method steps does not preclude the presence of additional method steps or intervening method steps between those steps expressly identified. Similarly, it is also to be understood that the mention of one or more components in a device or system does not preclude the presence of additional components or intervening components between those components expressly identified.

Embodiments of this disclosure include sorbent for use in a CCS process, particularly CO_2/H_2O displacement desorption, and methods for creating a more hydrophobic surface on these sorbents. FIG. 1 demonstrates a simplified system of CO_2/H_2O displacement desorption, in which a sorbent of this disclosure might be applied. System 100 includes two sorbent bed positions, 101 and 102, in which the sorbents of this disclosure would be placed. Sorbent bed position 101 contains a sorbent that is initially CO_2 poor. A CO_2 rich stream, 110, e.g. a flue gas feed from a combustion source, passes across sorbent bed 101, which absorbs the CO_2 , and a CO_2 depleted stream exits the bed. Once sorbent bed 101 is saturated, it can move to sorbent bed position 102. A steam feed 120 containing water vapor, can enter the CO_2 saturated sorbent bed 102 and cause desorption and displacement of the CO_2 from the sorbent. The exit gas stream is then a CO_2 rich stream that can then be further processed. Once sorbent bed 102 is regenerated, it can return to position 101. Several applications of this system have been demonstrated, such as in U.S. Pat. Nos. 9,504,955; 9,446,343; 9,539,540; and 9,527,029.

The typical sorbent used in CO_2/H_2O displacement desorption is an alkali metal salt impregnated on an aluminum oxide catalyst, particularly using a potassium salt. K_2CO_3/Al_2O_3 is a preferred sorbent currently. In the CO_2/H_2O displacement desorption process, steam usage is divided into two portions. One portion is used to drive off the CO_2 absorbed on the sorbent. Another portion is water absorbed on the sorbents via hydrogen binding to the hydroxyl groups of the sorbents. This second portion is effectively a wasteful or parasitic portion, and does not drive the process. Hydroxyl group concentrations and hydrophobic properties of the sorbents are key factors controlling H_2O uptake on sorbents.

Thus, key technical challenges in CO_2 displacement desorption process includes increasing sorbent's CO_2 sorption capacity and minimizing steam usage. Steam generation requires intensive energy consumption and accounts for the large portion of operating costs. Hydrophobic sorbents can minimize parasitic amount of water absorbed on the sorbents and reduce steam usage in CCS operation.

This disclosure includes silicon-modified sorbents, and methods of making the same. In particular, the disclosure includes a silicon-modified CO_2/H_2O displacement desorption sorbent, which comprises an aluminum compound support, an alkali metal salt impregnated on the aluminum compound support, and a silicon source capping at least a portion of the hydroxyl positions on the aluminum compound support. The silicon source can include a silica impregnated on the aluminum compound support, or an organosilyl moiety.

This disclosure includes a method for reducing parasitic water sorption/desorption for CO_2/H_2O displacement desorption sorbents, which includes surface modifying a sorbent with a silicon source. The sorbent can be an aluminum compound impregnated with an alkali metal, and the silicon

source can be an organosilyl moiety added to the sorbent after impregnating with the alkali metal or a silica added to the aluminum compound prior to impregnating with the alkali metal.

This disclosure includes a method for preparing a hydrophobic CO₂/H₂O displacement desorption sorbent, including the steps of impregnating an aluminum compound support with silica, drying and then calcining the silica-impregnated support, depositing an alkali metal salt on the silica-aluminum support, and calcining the support to form the sorbent.

This disclosure also includes a method for preparing a hydrophobic CO₂/H₂O displacement desorption sorbent, including the steps of preparing an aluminum compound mixture; drying and then calcining the mixture to form a support; depositing an alkali metal salt on the support; calcining the support to form the sorbent, and treating the sorbent with an organo silyl moiety.

The sorbents and methods can include an organosilyl moiety or reagent. One exemplary but non-limiting example of an organo silyl moiety is a trimethylsilyl group, i.e. TMS. Organosilyl moieties of the disclosure are silicon moieties that can bond to a hydroxyl group via the silicon atom. The organosilyl moiety can typically be a mono-, di-, or tri-organosilyl moiety, or can be a mono-alkyl, di-alkyl, or trialkyl silyl moiety. Exemplary alkyl groups in the organosilyl moieties can include methyl, ethyl, propyl, or butyl, or aryl, branched or unbranched. The alkyl groups in a di- or tri-silyl moiety can be the same or different. By way of example, the organosilyl moiety could be a trimethyl silyl group capping an oxygen in the support, or could be a di-methyl silyl group that is bound to two oxygens. Preferably, the organo silyl moiety is a trimethylsilyl, ethyl-dimethyl-silyl, diethyl-methyl-silyl, or triethylsilyl, more preferably trimethyl silyl.

One of skill in the art would appreciate that an organosilyl moiety that has reacted with a surface would be described as the fragment bound to the surface. Alternatively, the organosilyl moiety that is used in a method would be added as an organosilyl fragment bound to, typically, a leaving group. Traditional leaving groups for organosilyl fragments would include halides, triflates, tosylates, dialkylaminos, (e.g. N,N-Diethyl-1,1,1-trimethylsilylamine) and the such. Thus, the organosilyl moiety in a method can be organosilyl halides, organosilyl triflates, organosilyl tosylates, or organosilyl-di-alkyl amine, preferably organosilyl halides or organosilyl triflates, and more preferably organosilyl halides.

The sorbents and methods can include silica impregnated on the support. Silica can be added to an aluminum oxide compound and mixed prior to extruding, drying and calcining the aluminum oxide compound. Silica includes silica gels and oligomeric siloxanes, such as polydimethylsiloxane-co-methylphenylsiloxane, or other alkyls substituted for methyl, or mixed alkyls; hexamethyldisiloxane or other alkyls or mixed any alkyls; or aminofunctional oligomeric siloxane (such as Hydrosil). The silica can comprise at least about 5 wt % of the support, at least about 7 wt % of the support, at least about 8 wt % of the support, or at least about 10 wt % of the support. The silica can comprise up to about 20 wt % of the support, up to about 18 wt % of the support, or up to about 15 wt % of the support. The silica can be 5% to 20% by weight of the support, or 7% to 15% by weight of the support.

In the disclosure, the aluminum compound support includes any general aluminum oxide type compound, such as one of ordinary skill in the art would use in making

aluminum oxide-type support structures. In an embodiment, the aluminum compound support can be comprises aluminum oxide, aluminum oxide hydroxide, aluminum hydroxide, boehmite, or pseudoboehmite. The aluminum oxides, oxide hydroxides, and hydroxides can include: aluminum oxides including γ -aluminum oxide, θ -aluminum oxide, corundum (Al₂O₃); aluminum oxide hydroxides such as diaspore (α -AlO(OH)), boehmite or böhmite (γ -AlO(OH)), akdalaite, including 5Al₂O₃·H₂O and 4Al₂O₃·H₂O, also called tohdite; and aluminum hydroxides such as gibbsite, hydrargillite (hydrargyllite), bayerite, doyleite, nordstrandite, including α -Al(OH)₃, β -Al(OH)₃, γ -Al(OH)₃. In some preferred embodiments, the aluminum compound support comprises aluminum oxide hydroxide compounds, particularly, boehmite, or pseudoboehmite. While traditional Al₂O₃ compounds, as well as other aluminum oxide type compounds can work effectively, and without wishing to be bound by theory, the boehmite and pseudoboehmite compounds appear to be more effective in part because of the added hydroxylation of the aluminum composition, prior to drying and optionally calcining the support/extrudate.

An embodiment of the disclosure also includes impregnating the support with an alkali metal salt, or a sorbent that contains an alkali metal salt. This alkali metal salt can alternatively be described as the impregnating metal salt, because it is added to the support via impregnation to form the sorbent. By alkali metal salt is meant a Group 1 metal (group IA), including lithium (Li), sodium (Na), potassium (K), rubidium (Rb), and cesium (Cs). The alkali metal salt (i.e. impregnated alkali salt) can include lithium, sodium, potassium, rubidium, or cesium, or combinations thereof. The alkali metal salt can include lithium, sodium, potassium, or cesium, or combinations thereof. The alkali metal salt can include lithium, sodium, or potassium, or combinations thereof. The alkali metal salt can include potassium or sodium. The alkali metal salt can include potassium and sodium.

The amount of alkali metal salt, or the amount of alkali metal salt added to the support via impregnation during the method of making the support, can be at least about 5 wt % of the sorbent, at least about 6 wt % of the sorbent, at least about 7 wt % of the sorbent, at least about 8 wt % of the sorbent, at least about 9 wt % of the sorbent, at least about 10 wt % of the sorbent, at least about 11 wt % of the sorbent, or at least about 12 wt % of the sorbent. The percent weight of alkali metal is presented as weight M₂O as a percentage of the total weight of the sorbent.

One of ordinary skill would understand that alkali metal salt in the context of this disclosure implies the alkali metal cation. As such, synonymous terms include alkali metal compound, alkali metal salt, alkali metal ion, alkali metal cation, an alkali salt, alkali ion, alkali compound, or alkali cation. The alkali metal salt can also in the context of this disclosure be referred to as an alkali metal composition.

Because the alkali metal salt is a cation, it will necessarily have a counterion, i.e. an anion. However, the nature of that anion is not a limiting issue. On the sorbent, particularly during operation, the anion can be a carbonate or bicarbonate counterion, or a hydroxyl or oxide anion that is part of the support to which the alkali metal is impregnated upon. Moreover, during preparation of the sorbents, and also as part of the sorbent when the salt is impregnated on the support, or when it's included as part of the extrudate, the alkali metal cation can have any counteranion one of ordinary skill would use. Nonlimiting examples of the anion can be hydroxides, halides, carbonates, bicarbonates, nitrates, nitrite, phosphate, hydrogen phosphate, dihydrogen phos-

phate, and organic acid salts including but not limited to acetate citrate, gluconate, and benzoic acid, etc.

Another embodiment of the disclosure can include the addition of an alkali metal salt to the aluminum compound during mixing to prepare the initial support. The aluminum compound and an alkali metal salt can be mixed together to form a dough which can be extruded, dried and optionally calcined. This alkali metal salt can be described as an extrudate alkali metal salt since it is contained within the extrudate that is used to make the support. As discussed in a co-pending provisional application filed by the same entity on the same day, and titled HIGH PERFORMANCE CCS SORBENTS AND METHODS OF MAKING SAME, which is incorporated by reference in its entirety as if set forth herein, an alkali metal can be introduced to the aluminum compound during mixing to form the dough, extruded, and dried and calcined to form the support. The extrudate alkali metal salt can be any alkali metal salt. The extrudate alkali metal salt can be a lithium salt, a sodium salt, a potassium salt, or combinations thereof. Preferably the alkali metal salt added to the mixture includes a potassium salt, a sodium salt, or both a potassium salt and a sodium salt. Once the extrudate is dried and calcined, next impregnation steps can occur, e.g. the impregnation of silica, or the impregnation of the impregnated alkali metal and eventual organosilyl treatment.

In some instances, the impregnating alkali metal salt can be two different alkali metal salts. For example, impregnating both potassium and sodium can provide improved performance and stability over impregnating with only one alkali metal salt, including particularly only potassium metal salts. As discussed in a co-pending provisional application filed by the same entity on the same day, and titled MIXED METAL SORBENTS FOR CO₂/H₂O DISPLACEMENT DESORPTION, which is incorporated by reference in its entirety as if set forth herein, poisoning effects and improved performance can be achieved if two salts can be applied as the impregnating salts.

Another embodiment of the disclosure can include forming the initial support by preparing and extruding a dough to form an extrudate, drying the extrudate, and then calcining the support at about 120° C. to 500° C. forming a support prior to the addition of an impregnating alkali metal salt. Preferably the calcining can be at 200° C. to 400° C., or at 250° C. to 350° C. As discussed in a co-pending provisional application filed by the same entity on the same day, and titled CALCINATION OF CO₂/H₂O DISPLACEMENT DESORPTION SORBENTS, which is incorporated by reference in its entirety as if set forth herein, the lower calcination temperatures can provide better support for the techniques disclosed herein.

EXAMPLES

The following examples are illustrative, but not limiting, of the methods and compositions of the present disclosure. Other suitable modifications and adaptations of the variety of conditions and parameters normally encountered in the field, and which are obvious to those skilled in the art, are within the spirit and scope of the disclosure. All patents and publications cited herein are fully incorporated by reference herein in their entirety.

Example 1

Preparation of (9.9% K₂O+6.5% Na₂O/Al₂O₃)-
TMSCl

The aqueous solution containing sodium and potassium carbonates was prepared by dissolving Na₂CO₃ and K₂CO₃

in distilled H₂O. The sorbent was prepared by incipient wetness. 17.275 g of potassium carbonate and 13.248 g of sodium carbonate were dissolved in 60.0 g of di-H₂O. The total solution volume of Na₂CO₃ and K₂CO₃ adjusted with distilled water was 82.7 ml. 100.0 g of alumina extrudates were impregnated with the solution by incipient wetness. The sample was dried in air at 250° F. for 16 hours and calcined in air at 1000° F. for 6 hours. The furnace was ramped at rate of 5° F./min. During the calcination, the air flow was adjusted at 5 volume/volume solid/minute.

The sample of 9.9% K₂O+6.5% Na₂O/Al₂O₃ was impregnated with 50 ml of trimethylsilane chloride (TMSCl) solution. The TMSCl tetrahydrofuran solution concentration was 1.0 M. After impregnation, the sample was placed in the vacuum drying oven at room temperature for 4 hours, and at 151° F. with nitrogen flow overnight to remove any residual tetrahydrofuran solvent.

Example 2

Preparation of (Na₂CO₃+K₂CO₃) Supported on
SiO₂/Al₂O₃

The solution containing hydrosil was prepared by mixing 66.65 g of hydrosil in 30 g of water. The total volume of hydrosil was adjusted with water until the volume of the solution reached to 99.18 ml. 120 g of Al₂O₃ extrudates were impregnated with the hydrosil aqueous solution by incipient wetness. The sample was dried in air at 120° C. for 16 hours. The sample was calcined in air at 1000° F. for 6 hours. The furnace was ramped at rate of 5° F./min. During the calcination, the air flow was adjusted at 5 volume/volume solid/minute. SiO₂ loading on Al₂O₃ support was 10 wt %.

SiO₂ treated Al₂O₃ support was used for deposition of sodium and potassium carbonates. The aqueous solution containing sodium and potassium carbonates was prepared by dissolving Na₂CO₃ and K₂CO₃ in distilled H₂O. The sorbent was prepared by incipient wetness. 17.275 g of potassium carbonate and 13.248 g of sodium carbonate were dissolved in 50.0 g of di-H₂O. The total solution volume of Na₂CO₃ and K₂CO₃ adjusted with distilled water was 74.1 ml. 100.0 g of SiO₂ treated Al₂O₃ support was impregnated with the solution by incipient wetness. The sample was dried in air at 250° F. for 16 hours and calcined in air at 1000° F. for 6 hours. The furnace was ramped at rate of 5° F./min. During the calcination, the air flow was adjusted at 5 volume/volume solid/minute. The sorbent contains 9.9% K₂O and 6.5% Na₂O as K and Na loadings.

Example 3

Preparation of (Na₂CO₃+K₂CO₃) Supported on 10
wt % Al₂O₃ Treated SiO₂

The solution containing aluminum isopropoxide was prepared by dissolving 53.40 g of aluminum isopropoxide in 50 ml of isopropanol. The total volume of aluminum isopropoxide was adjusted with isopropanol until the volume of the solution reached to 101.5 ml. 120.0 g of silica extrudates were impregnated with the aluminum isopropoxide solution by incipient wetness. After impregnation, the sample was placed in the vacuum drying oven at 50° C. for 16 hours to remove residual isopropanol solvent. The sample was dried again in air at 120° C. for 16 hours. The sample was calcined in air at 1000° F. for 6 hours. The furnace was ramped at rate

of 5° F./min. During the calcination, the air flow was adjusted at 5 volume/volume solid/minute. Al₂O₃ loading on SiO₂ support was 10 wt %.

Al₂O₃ treated SiO₂ support was used for deposition of sodium and potassium carbonates. The aqueous solution containing sodium and potassium carbonates was prepared by dissolving Na₂CO₃ and K₂CO₃ in distilled H₂O. The sorbent was prepared by incipient wetness. 17.275 g of potassium carbonate and 13.248 g of sodium carbonate were dissolved in 50.0 g of di-H₂O. The total solution volume of Na₂CO₃ and K₂CO₃ adjusted with distilled water was 76.0 ml. 100.0 g of Al₂O₃ treated SiO₂ support were impregnated with the solution by incipient wetness. The sample was dried in air at 250° F. for 16 hours and calcined in air at 1000° F. for 6 hours. The furnace was ramped at rate of 5° F./min. During the calcination, the air flow was adjusted at 5 volume/volume solid/minute. The sorbent contains 9.9% K₂O and 6.5% Na₂O as K and Na loadings.

Example 4

CO₂ Sorption/Steam Displacement Fixed Bed Testing

Simulated natural gas flue gas during fixed bed testing contained 13.6% CO₂ and 15.3% H₂O balanced with N₂. The fixed bed volume is 100 cc. With the simulated natural gas conditions the flue gas space velocity during screening conditions was 10.56 SCCM/g for 9 minutes and steam regeneration space velocity was 3.74 SCCM/g for 9 minutes. The temperature during adsorption was about 140° C., increasing to approximately 153° C. during sorbent regeneration.

In the single fixed bed, all flow controllers were calibrated to obtain high accuracy in gas flowrates. Whenever a gas is not in use, the flow controller is completely shut to prevent any gas leakage. During adsorption cycle, N₂ and CO₂ are mixed with steam provided by 500 cc syringe pump. The feed enters the bed by down-flow through a 3-way valve and exits through another 3-way valve. The outlet gas/steam moves through a chiller, and the steam is condensed, collected and measured by an online scale. N₂ and CO₂ gases pass the chiller and exit to a ZRE CO₂ analyzer which measures the breakthrough CO₂ concentration. During regeneration cycle, both the 3-way valves are switched to allow steam controlled by 1000 cc syringe pump to enter the bed by up-flow and exit via a different path toward a second chiller. The steam is condensed and collected by online scale for measurement of water out in regeneration. CO₂ passes the chiller and is diluted with N₂ before entering the ZRE CO₂ analyzer which detects the desorbed CO₂ concentration. Both syringe pumps are continuously running through a 3-way valve which directs the steam either through the bed or to a by-pass line. The downstream N₂ is also used to remove/flush out the condensed water in the exit line at the end of each cycle.

Results and Discussion

The key technical challenges in CO₂ displacement desorption process are how to increase sorbent's CO₂ sorption capacity and minimize steam usage. Steam generation requires intensive energy consumption and account for the large portion of operating costs. Steam usage in the displacement desorption is divided into two portions. One portion is used to drive off CO₂ absorbed on the sorbent. Another portion is water absorbed on the sorbents via hydrogen binding to the hydroxyl groups of the support, which is wasteful. Hydroxyl group concentrations and

hydrophobic properties of the sorbents are key factors controlling H₂O uptake on sorbents.

The sorbent of (9.9% K₂O+6.5% Na₂O/Al₂O₃)-TMSCl was prepared by impregnating the sample of 9.9% K₂O+6.5% Na₂O/Al₂O₃ with trimethylsilane chloride (TMSCl) solution. TMSCl treatment was designed to cover hydroxyls of the sorbent to minimize parasitic H₂O on sorbents. It can be seen from FIG. 2, the H₂O/CO₂ molar ratio was reduced from the parent sample of 4.31 to 3.50 of TMSCl treated sample. 19% reduction of water usage in the CCS displacement desorption. The sorbent CO₂ sorption capacity was also reduced from 1.03 wt % to 0.88 wt %.

FIG. 3 shows CCS performance comparisons of sample of Na₂CO₃ and K₂CO₃ supported on 10% SiO₂/Al₂O₃ (MC-19052) and sample of Na₂CO₃ and K₂CO₃ supported on Al₂O₃ (MC-18775). Because of poor dispersions of Na₂CO₃ and K₂CO₃ on silica surface, Na₂CO₃ and K₂CO₃ are preferentially dispersed on alumina surface. Unoccupied support surfaces are predominately hydrophobic silica surfaces. When Na₂CO₃ and K₂CO₃ are supported on 10% SiO₂/Al₂O₃ (MC-19052), its H₂O/CO₂ molar ratio is 4.01, which is lower than that of 4.31 on the sample of Na₂CO₃ and K₂CO₃ supported on Al₂O₃ (MC-18775), 7% reduction of water usage. CO₂ sorption capacity was, however, slightly reduced to 0.98 wt % on MC-19052 from 1.03 wt % on sample MC-18775. When Na₂CO₃ and K₂CO₃ are supported on 10% Al₂O₃/SiO₂ (MC-19053), its CCS performance is significantly worse. The support surfaces of 10% Al₂O₃/SiO₂ are predominated by hydrophobic silica. Poor dispersions of Na₂CO₃ and K₂CO₃ on silica surface give low CO₂ sorption loading. The molar ratio of H₂O/CO₂ for sample MC-19053 is also high 7.79, due to relatively low CO₂ sorption on the sorbent.

It is to be understood that the embodiments and claims disclosed herein are not limited in their application to the details of construction and arrangement of the components set forth in the description and illustrated in the drawings. Rather, the description and the drawings provide examples of the embodiments envisioned. The embodiments and claims disclosed herein are further capable of other embodiments and of being practiced and carried out in various ways. Also, it is to be understood that the phraseology and terminology employed herein are for the purposes of description and should not be regarded as limiting the claims.

Accordingly, those skilled in the art will appreciate that the conception upon which the application and claims are based can be readily utilized as a basis for the design of other structures, methods, and systems for carrying out the several purposes of the embodiments and claims presented in this application. It is important, therefore, that the claims be regarded as including such equivalent constructions.

We claim:

1. A silicon-modified CO₂/H₂O displacement desorption sorbent, comprising an aluminum compound support; an alkali metal salt impregnated on the aluminum compound support; and 5% to 20% by weight of silica capping hydroxyl positions on the impregnated aluminum compound support.
2. The sorbent of claim 1, comprising 7% to 15% by weight of silica capping hydroxyl positions on the impregnated aluminum compound support.
3. The sorbent of claim 1, wherein the aluminum compound comprises aluminum oxide, aluminum oxide hydroxide, aluminum hydroxide, boehmite, or pseudoboehmite.

4. The sorbent of claim 1, wherein the alkali metal salt comprises a potassium salt, a sodium salt, a lithium salt, or combinations thereof.
5. The sorbent of claim 1, wherein the alkali metal salt is greater than about 5 weight % of the sorbent as M_2O . 5
6. The sorbent of claim 1, wherein the alkali metal salt is greater than about 8 weight % of the sorbent as M_2O .
7. A silicon-modified CO_2/H_2O displacement desorption sorbent, comprising an aluminum compound support; an alkali metal salt impregnated on the aluminum compound support; and 10
5% to 15% by weight of silica capping hydroxyl positions on the impregnated aluminum compound support.
8. The sorbent of claim 7, comprising 7% to 15% by weight of silica capping hydroxyl positions on the impregnated aluminum compound support. 15
9. The sorbent of claim 7, wherein the aluminum compound comprises aluminum oxide, aluminum oxide hydroxide, aluminum hydroxide, boehmite, or pseudoboehmite.
10. The sorbent of claim 7, wherein the alkali metal salt comprises a potassium salt, a sodium salt, a lithium salt, or combinations thereof. 20
11. The sorbent of claim 7, wherein the alkali metal salt comprises a potassium salt, a sodium salt, or combinations thereof. 25
12. The sorbent of claim 7, wherein the alkali metal salt is greater than about 5 weight % of the sorbent as M_2O .
13. The sorbent of claim 7, wherein the alkali metal salt is greater than about 8 weight % of the sorbent as M_2O . 30

* * * * *